

Fibertex nonwovens for bedding - standard range

Rev. 008-0918

Type	Weight (g/m ²)	Colours (Spec. no.)			Thickness (mm)	Breaking strength (N)		Elongation at 90 N (%)		Tear resistance (N)		Bending length (N)	
		White	Grey	Blue2	EN/ISO 9073-2	EN ISO 9073-18		EN ISO 9073-18		EN/ISO 9073-4		EN/ISO 9073-7	
Needlepunched						MD	CD	MD	CD	MD	CD	MD	CD
PocketLine	75	7003	7008	7007	0.55	220	265	18	23	105	85	5	5
CoverLine FR	75	7041	-	-	0.55	220	265	18	23	105	85	5	5
PocketLine LE	82	7017	7018	-	0.55	200	245	15	19	105	85	5	5
PocketLux	100	7000	-	-	0.65	265	355	16	19	135	105	5.3	5.3
100P20WL FLO	100	3361	-	-	0.85	200	250	30	30	135	100	N/A	N/A

Type	Weight (g/m ²)	Colour (Spec. no.)	Thickness (mm)	Tensile strength (N)		Elongation at 25 N (%)		Tear resistance (N)	
			EN/ISO 9073-2	EN/ISO 9073-3		EN/ISO 9073-3		EN/ISO 9073-4	
Spunbond		White		MD	CD	MD	CD	MD	CD
Spunbond 14g	14	HX0101400	N/A	33	16	N/A	N/A	N/A	N/A
Spunbond 40g	40	HX220400X	0.35	95	60	N/A	N/A	30	45
Spunbond 50g	50	IX220500X	0.4	120	80	2.5	7	40	60
Spunbond 60g	60	IX220600X	0.45	130	85	2	5.5	45	70
Spunbond 75g	75	IX220750X	0.5	150	100	2	4.5	55	80

MD: Machine direction CD: Cross direction

All values are target values

Widths/roll lengths:
Fibre composition:
Certificates:
Material safety data sheet (MSDS):

According to agreement
Polypropylene or blends of polypropylene and polyester
Oekotex Standard 100, ISO 9001, ISO 14001
Available on request

