

Product Data Sheet
Fibertex Geotextiles

Sheet no 400.60
Date June-20

Fibertex Geotextiles			F-10	F-20	F-22	F-22 2.0	F-25	F-31	F-32	F-35	F-38	F-46	F-40	F-50	F-59
Physical Properties															
Weight	EN ISO 9864	g/m ²	80	100	110	120	132	150	175	200	230	255	260	300	370
Thickness at 2 kPa	EN ISO 9863-1	mm	0.5	0.5	0.6	0.7	0.7	0.8	0.8	1.0	1.2	1.2	1.2	1.6	1.6
Mechanical Properties															
Static puncture (CBR-test)	EN ISO 12236	N	950	1100	1500	1500	2000	2100	2650	3000	3400	3500	3125	4500	5100
Tensile strength long. dir.	EN ISO 10319	kN/m	5.9	6.8	8.0	8.5	11.5	12.0	15.0	17.0	20.0	21.2	18.0	25.0	30.0
Tensile strength trans. dir.	EN ISO 10319	kN/m	5.4	6.6	8.0	8.3	11.5	12.0	15.0	17.0	20.0	23.4	18.0	25.0	30.0
Elongation at break long. dir.	EN ISO 10319	%	40	35	40	35	45	40	45	50	50	56	50	50	50
Elongation at break trans. dir.	EN ISO 10319	%	50	45	55	45	55	50	55	60	60	56	60	55	55
Dynamic Cone drop	EN ISO 13433	mm	>40	35	32	30	32	26	24	20	17	17	20	15	10
Protection efficiency at 300 kPa	EN 13719	%	-	2.6	2.5	2.5	2.4	2.5	2.3	2.5	2.3	2.4	2.1	2	2
Pyramid puncture resistance	EN 14574	N	-	70	80	80	110	200	160	250	290	300	220	270	400
Hydraulic Properties															
Permeability at 50 mm WH	EN ISO 11058	m/sec	0,1	0,09	0,07	0,08	0,07	0,05	0,04	0,04	0,04	0,03	0,04	0,03	0,02
Permittivity at 50 mm WH	EN ISO 11058	sec ⁻¹	2,0	1,8	1,4	1,6	1,4	1,0	0,8	0,8	0,8	0,6	0,8	0,6	0,4
Water flow at 50 mm WH	EN ISO 11058	l/sec/m ²	100	90	70	80	70	50	40	40	40	30	40	30	20
Velocity index at 100 mm WH	EN ISO 11058	m/sec	0,16	0,14	0,12	0,13	0,12	0,08	0,07	0,07	0,06	0,05	0,07	0,05	0,03
Water flow at 100 mm WH	EN ISO 11058	l/sec/m ²	160	140	120	130	120	80	70	70	60	50	70	50	30
Transmissivity	EN ISO 12958	10 ⁻⁶ m ² /sec	0,1	0,3	0,3	0,6	0,6	0,4	0,8	1,1	1,5	1,1	1,0	1,5	1,6
Water flow capacity	EN ISO 12958	l/hour/m	0,5	1,0	1,0	2,0	2,0	1,4	2,7	4,0	5,4	4,0	4,0	5,0	6,0
Pore size, O _{90%}	EN ISO 12956	micron	100	100	85	90	70	75	85	70	65	70	70	65	70
Standard Dimensions															
Width	m	2 / 4 / 5	2 / 4 / 5	2 / 4 / 5	2 / 4 / 5	1 / 2 / 4 / 5	2 / 4 / 5	2 / 4 / 5	4 / 5	4 / 5	4 / 5	4 / 5	2 / 4 / 5	4 / 5	5
Length	m	100	100	100	100	50 / 100	100	100	100	100	100	100	100	100	100
Roll diameter	cm	26	26	28	28	28	28	32	33	35	35	35	36	42	34
Roll weight at maximum standard dimension	kg	40	50	55	60	66	66	75	88	100	115	128	130	150	185

Above technical values are mean values based on measurements in current production and test results from independent test institutes.
Fibertex reserve the right to make changes without notice. Contact fibertex@fibertex.com for latest version.

Fibertex Geotextiles

Fibertex Geotextiles are used in building and construction works for separation, filtration, drainage, protection, stabilization and reinforcement.
Fibertex Geotextiles are made of virgin polypropylene fibres added HALS UV stabilizer according to EN 12224.

The basic strength of Fibertex Geotextiles is obtained by needle-punching the PP-fibres, which gives strong elastic bonding between the fibres.
Due to the unique production process all Fibertex Geotextiles are added a thermal treatment unless marked with:

M: Needlepunched only

Quality Management

Fibertex production control is certified CE-marking level 2+ for all geotextiles.



Fibertex Nonwovens A/S is certified according to the international quality management system EN ISO 9001 as well as the environmental management system EN ISO 14001.

Specifications for Tender

The geotextile should be Fibertex typeor comparable type.
The material should be needlepunched PP with a CBR puncture resistance ofN, acc. to EN ISO 12236 and a Wide-width tensile elongation of% acc. EN ISO 10319.
Water permeability should be l/sec/m² acc. to EN ISO 11058 and Pore size d90%micron acc. EN ISO 12956. The geotextile supplier must be certified acc. to ISO 9001 and ISO 14001, and the products must be CE-marked.

Product Data Sheet
Fibertex Geotextiles

Sheet no 400.60
Date June-20

Fibertex Geotextiles			F-200M	F-300M	F-400M	F-500M	F-600M	F-800M	F-1000M	F-1200M
Physical Properties										
Weight	EN ISO 9864	g/m ²	200	300	400	500	600	800	1000	1200
Thickness at 2 kPa	EN ISO 9863-1	mm	2	2.5	3.2	3.5	4.5	6	7	7
Mechanical Properties										
Static puncture (CBR-test)	EN ISO 12236	N	2600	3900	5200	6500	7800	10400	13000	15000
Tensile strength long. dir.	EN ISO 10319	kN/m	16,5	25	30	38	49,5	58,5	56,0	65,0
Tensile strength trans. dir.	EN ISO 10319	kN/m	16,5	25	36	45	49,5	73,5	90,0	100,0
Elongation at break long. dir.	EN ISO 10319	%	65	60	75	75	75	80	90	85
Elongation at break trans. dir.	EN ISO 10319	%	80	70	75	75	80	80	70	65
Dynamic Cone drop	EN ISO 13433	mm	20	16	10	8	5	0	0	0
Protection efficiency at 300 kPa	EN 13719	%	2,4	2,3	1,8	1,7	1,6	1,2	0,8	0,4
Pyramid puncture resistance	EN 14574	N	170	260	400	520	650	900	1200	1500
Hydraulic Properties										
Permeability at 50 mm WH	EN ISO 11058	m/sec	0,08	0,05	0,05	0,03	0,03	0,03	0,02	0,015
Permittivity at 50 mm WH	EN ISO 11058	sec ⁻¹	1,6	1	1	0,6	0,6	0,6	0,4	0,3
Water flow at 50 mm WH	EN ISO 11058	l/sec/m ²	80	50	50	30	30	30	20	15
Velocity index at 100 mm WH	EN ISO 11058	m/sec	0,13	0,07	0,07	0,06	0,05	0,048	0,032	0,024
Water flow at 100 mm WH	EN ISO 11058	l/sec/m ²	130	70	70	60	50	48	32	24
Transmissivity	EN ISO 12958	10 ⁻⁹ m ² /sec	3,5	4	3	4,3	8,3	10	10	12
Water flow capacity	EN ISO 12958	l/hour/m	12,6	15	12	15	29,9	36	36	43
Pore size, O _{90%}	EN ISO 12956	micron	100	70	80	65	70	80	70	60
Standard Dimensions										
Width		m	4 / 5	4 / 5	5	5	5,5	5,5	5,5	5,5
Length		m	100	100	100	100	100	50	50	50
Roll diameter		cm	48	60	60	72	73	58	69	72
Roll weight at maximum standard dimension		kg	100	150	200	250	330	220	275	330

Above technical values are mean values based on measurements in current production and test results from independent test institutes.

Fibertex reserve the right to make changes without notice. Contact fibertex@fibertex.com for latest version.

Fibertex Paving Fabric			AM-2
Weight	EN ISO 9864	g/m ²	145
Thickness at 2 kPa	EN ISO 9863-1	mm	1,05
Static puncture (CBR-test)	EN ISO 12236	N	1500
Tensile strength	EN ISO 10319	kN/m	8
Elongation at break	EN ISO 10319	%	55/55
Dynamic Cone drop	EN ISO 13433	mm	25
Bitumen retention	EN 15381	kg/m ²	1,3
Dimensions	Width	m	3,75/5,0
	Length	m	100
	Roll diameter	cm	35