

Product Data

Fibertex needlepunch for furniture

Rev. 012-0922

Type	Weight (g/m²)							Thickness (mm)	Trapez tear strength (N)		Breaking strength (N)		Elongation at break (%)		Flammability test		Oeko-tex® Standard 100
								EN ISO 9073-2	EN ISO 9073-4		EN ISO 9073-18		EN ISO 9073-18		Cigarette test BS5852: Part 1:1979 *	Match test BS5852: Part 1:1979 **	
		Light beige	Sand	Brown	Grey	Anthracite	Black		MD	CD	MD	CD	MD	CD			
80WL	80				3050	3001	3107	0.5	60	40	130	130	35	40			✓
F-Tex 10	95				QG_001470	QG_001490	QG_001419	1	120	80	190	220	55	60	✓	✓	✓
100WL	100		3212	3151	3052	3002	3102	0.6	100	60	200	200	45	50			✓
100WL FR	100			0528	3098		0547	0.6	100	60	200	200	45	50			✓
100WL BH-1	100	3020	3213	3152	3054		3103	0.9	110	80	180	180	50	55			✓
100WL BH-1 FR	100				5109		3249	0.9	110	80	180	180	50	55	✓	✓	✓
F-Tex 11	110				QG_001469	QG_001407	QG_001608	1.1	140	90	220	280	55	60	✓	✓	✓
F-Tex 12	120				QG_001432	QG_001408	QG_001360	1.2	150	100	250	320	55	60	✓	✓	✓
125WL	125	3257	3218	3153	3053	0619	3104	0.7	130	80	260	320	40	40			✓
125WL BH-1	125	3255	3210	3154	3062		3105	1.0	140	100	240	300	45	45			✓
125WL BH-1 FR	125	3085	3232	3033	3127		3035	1.0	140	100	240	300	45	45	✓	✓	✓
150WL	150				3055			0.8	180	120	350	450	45	45			✓
150WL BH-1	150	3253	3229	3155	3063		3106	1.2	180	130	350	450	45	45			✓
230WL	230				3056			1.2	300	220	500	700	55	55			✓
230WL BH-1	230				3057			1.7	300	200	500	700	55	55			✓

Indicative values

WL: Thermally bonded on both sides
 BH-1: One side with textile-like surface, other side thermally bonded
 FR: Fire retardant
 MD: Machine direction
 CD: Cross direction

* Products PASS the Cigarette test for invisible parts, Schedule 4 Part 2
 ** Products PASS the Match test for invisible parts, Schedule 5 Part 3

Roll width tolerance:
 Cut sheets width tolerance:
 Widths:
 Standard roll length:
 Standard fastening on tubes:
 Standard packaging:

+/- 1 cm
 +/- 1 cm
 According to agreement
 100 lin. mts.
 Staples
 HDPE plastic

Fibre composition:
 Embossed pattern:
 Cut sheets:
 Material safety data sheet (MSDS):

Polypropylene, polyester or blends of these
 Exclusive embossed pattern is available on BH-1 surfaces for types of min. 125 g/m²
 Fibertex can be delivered in rectangular cut sheets
 On request