

Geogrid/nonwoven composite



NAUE GmbH & Co. KG
Gewerbestr. 2
32339 Espelkamp-Fiestel
Germany

Phone: +49 5743 41-0 Fax: +49 5743 41-240
E-Mail: info@naue.com Internet: www.naue.com

Combigrid® 40/40 Q6 R 156 C

Product description:

Composite of a laid geogrid made of stretched, monolithic polyester (PET) flat bars with welded junctions and a mechanically bonded and calendered filter geotextile welded within the geogrid structure, used for stabilisation and reinforcement of soils in many fields of infrastructure, environmental protection and hydraulic engineering

Property	Test method*	Unit	
Geogrid			
Raw material	-	-	polyester (PET), transparent
Mass per unit area	EN ISO 9864	g/m ²	approx. 360
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	≥ 40 / ≥ 40
Elongation at nominal strength, md / cmd**	EN ISO 10319	%	≤ 7 / ≤ 7
Tensile strength at 1% elongation, md / cmd**	EN ISO 10319	kN/m	10.0 / 10.0
Tensile strength at 2% elongation, md / cmd**	EN ISO 10319	kN/m	18.0 / 18.0
Tensile strength at 5% elongation, md / cmd**	EN ISO 10319	kN/m	32.0 / 32.0
Radial stiffness @0.5% strain***	EN ISO 10319	kN/m	≥ 634
Aperture size, md x cmd**	-	mm x mm	approx. 34 x 33
Production specific elongation	-	%	0
Geotextile			
Raw material	-	-	polyester (PES), white
Mass per unit area	EN ISO 9864	g/m ²	150
Characteristic opening size	EN ISO 12956	µm	120
Water permeability - V _{H50} -Index - Flow rate _{H50}	EN ISO 11058	m/s l/(m ² s)	1.1 x 10 ⁻¹ 110
Detector tested	-	-	yes
Roll dimensions, width x length	-	m x m	4.75 x 100

*based on, **md = machine direction, cmd = cross machine direction; ***this test is performed by external laboratories and is not part of our regular quality control

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.