

TechGrid – TGC B 55

PRODUCT DATASHEET



TechGrid TGC series are knitted non-woven geotextile composites, incorporating high tenacity yarns in both directions. The high tenacity polyester yarns with low creep strain perform the reinforcement function, while the polypropylene needle punched non-woven geotextile provides both separation and drainage.

Physical Properties:	Units		TGC-55/55	Test Method
Composition	Knitted, high tenacity, polyester yarns			
¹ Tensile Strength (Ultimate)	MD/CD	kN/m	55	EN ISO-10319
Elongation @ Ultimate (±2)	MD/CD	%	10	
Tensile Strength @ 2% Strain	MD/CD	kN/m	9	
Tensile Strength @ 5% Strain	MD/CD	kN/m	22.5	
Reduction Factor (RF) and factor of safety (f_s) for calculation of MD Long-term Design Strength (LTDS):				
Creep (RF_{CR}) – 120 years design life at 20°C temperature			1.54	EN ISO
Installation damage with yarn facing soil (RF_{ID})	Sand/silt/clay		1.02	
Durability (RF_{CH}), 120 years design life at 20°C temperature, pH = 4 to 8.9			1.10	
Weathering (RF_w)	To be covered in 1 day		1.00	
Factor of safety for extrapolation of data for 120 years (f_s)			1.00	
LTDS – 120 YEARS: Sand/silt/clay for pH = 4 to 8.9		kN/m	31.8	
Hydraulic Properties:				
Water Permeability Normal to the Plane (-25)	l/m ² /s		112.0	EN ISO-11058
Apparent Pore Opening Size	µm		150	EN ISO-12956
Standard Roll Dimensions:				
Roll Width x Length	5m x 100m			

1. Minimum Average Roll Value (MARV).



To ensure this document contains the most up-to-date technical information available go to fibertex.com

+27 31 736 7100 | salesza@fibertex.com | fibertex.com